

m/s Beaulieu of Australia
64 Lahrs Rd, Ormeau Q/Ld 4208
Attn: MS Sue Schultz

TEST REPORT No. 155512C

LABORATORY REF: P155512C

CUSTOMER REFERENCE

TUSCAN SUN

Sample description as provided by customer

Mass/unit area **30 oz/yd²**

Construction Details **Tufted** Secondary Backing **Synthetic**

Style **Cut Pile**

Order No. **285395**

Pile Fibre Content **100% RESISTAIN SOLUTION DYED NYLON**

Colour **Cream**

Pile Height / mm

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10 of the Building Code of Australia.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date **Feb 2012**

Test Date **11 Jun 2012**

ASSEMBLY SYSTEM: OVER UNDERLAY 7 mm AIRSTEP FOAM.

The UNDERLAY used was **7 mm AIRSTEP FOAM**.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction Critical Radiant Flux **2.3 kW/m²**
Specimen 1 Width Direction Critical Radiant Flux **2.2 kW/m²**
Full tests carried out in the **Width** Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	2.2	2.5	2.1	2.3
Smoke Development Rate (%.min)	311	315	352	326

The values quoted below are as required by Specification C1.10 Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 2.3 kW/m²

MEAN SMOKE DEVELOPMENT RATE 326 percent-minutes

OBSERVATIONS: **The samples shrunk away from the heat source, ignited and burnt.**



M. B. Webb
Technical Manager

DATE: 11 Jun 2012

Performance & Approvals
Testing No. 15393
Accredited for compliance with ISO/IEC 17025.

PAGE 1 of 2

Clause 9 of AS/ISO 9239 Part 1

The values on Page 2 have no relevance to the Code.

1004 04 09

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	170	173	224	247	287	331	363	408	476	657	995	1439	1963					
2	183	185	211	252	281	301	359	392	467	662	800	1305						
3	195	198	295	315	344	364	380	422	491	675	961	1403	1821					

TESTS

BURNING CHARACTERISTICS

SMOKE PRODUCTION

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)	Maximum Light Attenuation (%)	Smoke Development Rate (%.min)
Initial Test: Length	71	309	623	2,109
Specimen Tests: Width				
1	69	311	630	311
2	69	315	590	315
3	70	352	650	352
Mean	69	326	623	326



ACCREDITED FOR
**TECHNICAL
COMPETENCE**

M. B. Webb
Technical Manager

DATE: 11 Jun 2012

Performance and Approvals
Testing No. 15393
**Accredited for compliance
with ISO/IEC 17025.**

The laboratory does not allow the use of this page of the report without the use of page 1.

This page alone has no validity under Clause 9 of AS/ISO 9239 Part 1

2004 04 09 0 18 June 2015