

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Beaulieu of Australia Limited  
166 Pearson Road  
Yatala QLD 4207

**Test Number :** 18-005557  
**Issue Date :** 11/01/2019  
**Print Date :** 14/01/2019  
**Order Number :** 30321

**Sample Description** Clients Ref : Ultra Tuff  
Level loop pile graphic carpet  
Colour : Blue  
Nominal Composition : Solution dyed Nylon  
Nominal Mass per Unit Area/Density : 20oz/yd<sup>2</sup>  
Nominal Thickness : Approx: 8mm

### AS/ISO 9239.1-2003

#### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 19/09/2018

Date Tested 11/01/2019

CHF Value	1	2	3	Mean
Length	7.0	9.1	9.5	8.5 kW/m <sup>2</sup>
Width	9.5	-	-	- kW/m <sup>2</sup>

HF-30 Value	1	2	3	Mean
Length	8.0	-	-	- kW/m <sup>2</sup>
Width	-	-	-	- kW/m <sup>2</sup>

Smoke Value	1	2	3	Mean
Length	33	10	19	21 %.min
Width	20	-	-	- %.min

Melting Yes

153062

30894

Page 1 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Beaulieu of Australia Limited  
166 Pearson Road  
Yatala QLD 4207

**Test Number :** 18-005557  
**Issue Date :** 11/01/2019  
**Print Date :** 14/01/2019  
**Order Number :** 30321

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23\pm 2^{\circ}\text{C}$  and relative humidity of  $50\pm 5\%$  for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

153062

30894

Page 2 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR